

DeWitt Company, Inc.
PRO 5 Specifications

TYPICAL PROPERTIES

TEST METHOD

Material		Polypropylene
Color		Black with a gold Stripe every 12"
Thickness		5.0 oz (average)
Permeability		12 gal/sqft/min
Grab Tensile Strength (lbs)	ASTM D-4632	Warp – 100 Fill – 60
Grab Elongation (%)	ASTM D-4632	Warp - 23 Fill – 17
Trapezoidal Tear (lbs)	ASTM D-4533	70 / 70
Mullen Burst (psi)	ASTM D-3786	85
UV Exposure		>70% after 2500 Carbon Arc hrs
Weatherometer		(5 year minimum) FEDTM 191-70%

Date: 01/12/03 This data sheet supersedes all previously issued data.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS, SUCH INFORMATION IS TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE AND RELIABLE AS THE DATE COMPLIED. HOWEVER NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. WE DO NOT ACCEPT LIABILITY FOR ANY LOSS OR DAMAGE THAT MAY OCCUR FROM THE USE OF THIS INFORMATION NOR DO WE OFFER ANY WARRANTY AGAINST PATENT INFRINGEMENT.